

# TECHNICAL DATA SHEET

## PRIMER 9800

Polymer based primer for consequent use with self-adhesive SealEco rubber membranes, and for priming porous substrates.

### Technical data

<b>Base:</b>	Primer based on a synthetic rubber and synthetic resins
<b>Colour:</b>	Black
<b>Consistence:</b>	Liquid
<b>Flash point:</b>	-20°C
<b>Viscosity (at 20°C):</b>	900 mPa.s
<b>Density (at 20°C):</b>	0,84 g/cm <sup>3</sup>
<b>Solids:</b>	36,30 %
<b>VOC content:</b>	532,3 g/l
<b>Shelf life:</b>	18 months in a well ventilated and dry storage place at temperatures in between +5°C and 30°C. Keep away from direct sunlight.



### Accessories



Handgun



Adapter E17



Handgun long  
61 cm



Hose

### Packaging

Weight (kg/pce)	Volume (L/pce)	Pieces/box	Pieces/pallet	Weight/pallet (kg)
0.9	1.07	12	30	349
4.2	5.0	N/A	72	328
12.5	14.88	N/A	33	438
19.2 (14.4 content)	19.1	N/A	24	486

Availability depending on country. Please contact your local supplier for more information.

### Coverage

125 - 250 g/m<sup>2</sup> depending on substrate.

### Directions for use

Primer 9800 is ready-for-use and must not be mixed with other products. The primer can only be applied in dry weather conditions at temperatures in between +5°C and 30°C. At temperatures between 5°C and 15°C SealEco recommends to pre-heat the primer to a maximum of 30°C prior to use. At all times, the temperature of the primer shall be >15°C when applying. Primer 9800 should be applied in a thin even layer with a stiff brush or roller or with a handgun and pressurized canister. Before unrolling the membrane, check that the primer is totally flashed off. Max. open time is 3 hours. When Primer 9800 was exposed to moisture a new layer should be applied. Equipment and tools can be cleaned with Cleaning Wash 9700, immediately after use. We recommend attending a training course before using the sprayable adhesive.

### Suitable substrats

Primer 9800 can be used on substrates such as: wood, concrete, cellular concrete, steel, bitumen and suitable insulation boards. Not to be used on EPS, XPS and softened PVC membranes. The substrate shall have a temperature of minimum +5°C, be clean, dry, and free from oil and grease. In case of porous substrates, Primer 9800 shall be applied twice. Let the first layer flash off before applying the second layer. Consult the installation manual for more instructions.

### Note

Product is extremely flammable packed in pressurized cannister. Make sure to read material safety data sheet before transport, storage or usage.

### Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check [www.sealeco.com](http://www.sealeco.com).