

# TEKNISKT DATABLAD

## SEALANT 5590

Neutral, elastisk enkomponents silikonbaserad fogmassa. Sealant 5590 har utmärkt vidhäftning på SelaEco gummi membran och de flesta andra underlag. Fogmassa används för repareringar och förseglag mot underlaget.



### Tekniska data

<b>Bas:</b>	Oxime
<b>Färg:</b>	Svart
<b>Konsistens:</b>	Paste
<b>Flampunkt:</b>	> 200°C
<b>Densitet (vid 20°C):</b>	1.25 g/cm <sup>3</sup>
<b>Hållbarhet:</b>	12 months in a well ventilated and dry storage place at temperatures in between +5°C and 30°C.

### Förpackning

Innehåll (ml/styck)	Stycken/låda	Vikt/låda (kg)	Lådor/pallet	Vikt/pallet (kg)
310 / patron	15	6,8	100	705
600 / foliekrov	12	9,8	60	613

Tillgänglighet kan variera beroende på land. Vänligen kontakta din lokala leverantör för mer information.

### Täckförmåga

6 m/patron - 12 m/ foliekrov.

### Arbetsbeskrivning

Sealant 5590 is a ready-to-use sealant specially developed for sealing profiles and seams. It can only be applied in dry weather conditions at temperatures in between +5°C and 30°C. At temperatures between 5°C and 15°C SealEco recommends to pre-heat the sealant to a maximum of 30°C prior to use. At all times, the temperature of the sealant shall be >15°C when applying. Sealant 5590 is applied with a caulking gun. Sealant 5590 that has not dried out yet can be cleaned with Cleaning Wash 9700. Once the sealant has totally cured it cannot be dissolved by cleaning and must be mechanically removed.

### Lämpliga underlag

Sealant 5590 provides an excellent adhesion on many materials, such as EPDM/Butyl rubber, wood, concrete, cellular concrete, bricks, aluminum and other metals. When applying on stones, discoloration of the stones may occur. The substrate shall have a temperature of minimum +5°C, be clean, dry, and free from oil and grease. Once a substrate has been in contact with Sealant 5590, Thermobond hot air welding or cold splicing is no longer possible. The membrane has to be grinded, so that all sealant is removed. Sealant 5590 can not be used on bitumen. In case of porous substrates, Primer 9800 should be applied and left to dry before applying Sealant 5590. Consult the installation manual for more instructions.

### Varning

Contact Adhesive 5000 är mycket lättantändligt. Konsultera MSDS för transport, lagring och användning.

### OBS!

Den senaste och enda giltiga versionen av detta tekniska datablad kan skickas till dig på begäran eller hittas på vår webbplats: [www.sealeco.com](http://www.sealeco.com).