

TECHNICAL DATA SHEET

THERMOBOND R SPLICE STRIP

The Thermobond R (Reinforced) Splice Strip is used for making connections between SealEco EPDM membranes and for detail works like flashings and upstands. The product is built up by a top layer of reinforced EPDM and a bottom layer of Thermobond. The recommended width for connections membrane to membrane is 150 mm.



Technical data

| Reinforcement: | Scrim of Polyester | | |
|----------------|---|--|--|
| Thickness: | 1.5 mm | | |
| Colour: | Black | | |
| Shelflife: | Store cool and dry in the original packaging. There are no limitations in shelf life. | | |

| Width (m) | Length (m) | Weight (kg/roll) | Max roll/pallet |
|-----------|------------|------------------|-----------------|
| 150 | 20 | 5.9 | 15x8 |
| 300 | 20 | 11.7 | 15x4 |
| 450 | 20 | 17.6 | 15x2 |
| 600 | 20 | 23.4 | 15x2 |
| 900 | 20 | 35.1 | 15x1 |

Directions for use

Thermobond R Splice Strips are used for connections between two SealEco EPDM membranes or for sealing flashings and upstands in roofing applications. Thermobond seaming technique is unique and patented by SealEco, and can only be used on SealEco EPDM mebranes. Thermobond is based on a thermoplastic rubber that can be seamed with conventional seaming methods for plastic material like hot air or hot wedge seaming. The Thermobond material is the base for a full range of accessories that gives good system solutions combining the unique properties of an elastomeric membrane with the seaming properties of the thermoplastics. Installations with Thermobond splicing are only authorised for fully trained installers. Consult the instruction manual before use.

Thermobond R Splicing will usually be used for splicing SealEco EPDM membranes in roofing applications. The EPDM membrane has to be clean and dry. Oxidized surfaces have to be grinded and cleaned with Cleaning Wash 9700. Splicing is possible between -15°C and 40°C. Splicing is not allowed during precipitation.

Note

Please read the MSDS before use.

Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check www.sealeco.com