

# TECHNICAL DATA SHEET

## THERMOBOND HOT MELT SEALANT 4MM X 30M

Thermobond Hot Melt Sealant is used to level differences in height at splice areas at T-joints and crossjoints with SealEco EPDM membranes.



### Technical data

<b>Product:</b>	TPE
<b>Colour:</b>	Black
<b>Diameter:</b>	4 mm
<b>Length:</b>	30 m
<b>Weight/roll</b>	0.92 kg
<b>Shelf life:</b>	Store cool and dry in the original packaging. There are no limitations in shelf life.

Availability depending on country. Contact your local supplier for more information.

### Directions for use

Thermobond Hot Melt Sealant is used to level differences in height at splice areas at T-joints and cross-joints and prevent capillarity. The sealant is part of the Thermobond accessories and is spliced with hot air. Thermobond seaming technique is unique and patented by SealEco, and can only be used on SealEco EPDM membranes. Thermobond is based on a thermoplastic rubber that can be seamed with conventional seaming methods for plastic material like hot air or hot wedge seaming. The Thermobond material is the base for a full range of accessories that gives good system solutions combining the unique properties of an elastomeric membrane with the seaming properties of the thermoplastics. Installations with Thermobond splicing are only authorised for installers fully trained by SealEco. Consult the instruction manual before use.

### Splicing conditions

Thermobond splicing can only be done on SealEco EPDM membranes. The EPDM membrane has to be clean and dry. Oxidised surfaces have to be grinded and cleaned with Cleaning Wash 9700. Splicing is possible between -15°C and 40°C. Splicing is not allowed during precipitation.

### Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check [www.sealeco.com](http://www.sealeco.com).