

TECHNICAL DATA SHEET

THERMOBOND R SPLICE STRIP

The Thermobond R (Reinforced) Splice Strip is used for making connections between SealEco EPDM membranes and for detail works like flashings and upstands. The product is built up by a top layer of reinforced EPDM and a bottom layer of Thermobond. The recommended width for connections membrane to membrane is 150 mm.



Technical data

Reinforcement:	Scrim of Polyester
Thickness:	1.6 mm
Colour:	Black
Shelf life:	Store cool and dry in the original packaging. There are no limitations in shelf life.

Packaging

Width (m)	Length (m)	Weight (kg/roll)	Max roll/pallet
150	20	5.9	15x8
300	20	11.7	15x4
450	20	17.6	15x2
600	20	23.4	15x2
900	20	35.1	15x1

Availability depending on country. Contact your local supplier for more information.

Directions for use

Thermobond R Splice Strips are used for connections between two SealEco EPDM membranes or for sealing flashings and upstands in roofing applications. Thermobond seaming technique is unique and patented by SealEco, and can only be used on SealEco EPDM membranes. Thermobond is based on a thermoplastic rubber that can be seamed with conventional seaming methods for plastic material like hot air or hot wedge seaming. The Thermobond material is the base for a full range of accessories that gives good system solutions combining the unique properties of an elastomeric membrane with the seaming properties of the thermoplastics. Installations with Thermobond splicing are only authorised for installers fully trained by SealEco. Consult the instruction manual before use.

Splicing conditions

Thermobond splicing can only be done on SealEco EPDM membranes. The EPDM membrane has to be clean and dry. Oxidised surfaces have to be grinded and cleaned with Cleaning Wash 9700. Splicing is possible between -15°C and 40°C. Splicing is not allowed during precipitation.

Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check www.sealeco.com.