


TECHNICAL DATA SHEET

THERMOBOND WATERSTOP

Thermobond Waterstop shall be used in tanking application when compartmentalising Elastoseal EPDM waterproofing membrane. Thermobond waterstop is installed to prevent spreading of water in case of damage to the membrane. The waterstop is produced in Thermobond that is a patented technique that enables heat welding to SealEco EPDM membranes.



Technical data

Base:	Thermoplastic elastomer
Density:	1.4 kg/m ²
Colour:	Black
Shelf life:	Store cool and dry in the original packaging. There are no limitations in shelf life.

Packaging

Width (mm)	Thickness (mm)	Length (m/roll)	Height (mm)	Anchoring ribs (pcs)
240	4.5	25	25	4

Availability depending on country. Contact your local supplier for more information.

Directions for use

Thermobond seaming technique is unique and patented by SealEco, and can only be used on SealEco EPDM membranes. Thermobond is based on a thermoplastic rubber that can be seamed with conventional seaming methods for plastic material like hot air or hot wedge seaming. The Thermobond material is the base for a full range of accessories that gives good system solutions combining the unique properties of an elastomeric membrane with the seaming properties of the thermoplastics. Installations with Thermobond splicing are only authorised for installers fully trained by SealEco. Consult the instruction manual before use.

Splicing conditions

Thermobond splicing can only be done on SealEco EPDM membranes. The EPDM membrane has to be clean and dry. Oxidised surfaces have to be grinded and cleaned. Splicing is possible between -15°C and 40°C. Splicing is not allowed during precipitation.

Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check www.sealeco.com.