

TECHNICAL DATA SHEET

EPDM FLASHING TAPE

EPDM Flashing Tape is made of an uncured EPDM laminated with a self-adhesive uncured rubber, and is used for detailing corners, pipe boots and T-joints on SealEco EPDM membranes. The tape provides immediate adhesion, is extremely flexible and can be formed to fit irregular shapes and surfaces. EPDM Flashing Tape should always be used in conjunction with Single Ply Primer.



Technical data

Base:	Synthetic Rubber
Colour:	Black
Thickness:	1.7 ± 10% mm
Cold bending temperature:	-40°C
Elongation at break:	> 300%
Shelf life:	12 months in a well ventilated and dry storage place at temperatures in between +5°C and 30°C.

Packaging

Width (mm)	Roll length (m)	Rolls/case (pcs)	Weight/case (kg)	Cases/pallet (pcs)
152	30.48	2	23.6	18
229	15.25	2	17.7	40
305	15.25	1	12.2	45
457	15.25	1	17.2	24

Availability depending on country. Please contact your local supplier for more information.

Directions of use

All surfaces should be clean, dry and free from creases or tension. If necessary, the EPDM membrane can be cleaned with Cleaning Wash 9700 before joining. Position the Flashing Tape with a minimal overlap of 80 mm. Mark the position of the Flashing Tape. Apply Single Ply Primer on the entire join area, according to the instructions. Wait until Single Ply Primer has flashed off. Do not leave exposed for longer than 20 minutes (at 20°C, 50% RH).

Place the Flashing Tape on the Single Ply Primer without enclosing air and deform the tape where necessary. Firmly press the Flashing Tape with a detail pressure roller and a 40 mm wide silicone roller. Seal all cut edges with Sealant 5590.

Flashing Tape should not be installed in temperatures below +5°C and above 30°C; during rain, mist or where there is a risk of condensation or strong winds. When applied between +5°C and 15°C SealEco recommends to store the Flashing Tape at room temperatures prior to use.

Consult our installation manuals for more information.

Note

Read the safety data sheet (MSDS) before usage.

Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check www.sealeco.com.