

TECHNICAL DATA SHEET

PREFABRICATION

RUBBERTOP S/ST/STT

RubberTop S/ST/STT is an elastomeric waterproofing membrane based on the rubber polymer EPDM. RubberTop S/ST/STT shall be used as waterproofing layer in roof constructions under ballast or adhered to the substrate, and for greenroofs.

RubberTop S/ST/STT provides a very long expected service life and is an environmental friendly product.



Technical data

Thickness	Weight
1.0 mm	1.1 kg/m ²
1.2 mm	1.4 kg/m ²
1.5 mm	1.7 kg/m ²

Rolls, RubberTop S

With RubberTop S, prefabrication should be performed with hotbond.

Thickness (mm)	Width (m)	Length (m)
1.0	1.70	25 / 125
1.2	1.70	25 / 100
1.5	1.70	25 / 75

Rolls, RubberTop ST/STT

With RubberTop ST/STT, prefabrication should be performed with hot air or hot wedge technology.

Thickness (mm)	Width (m)	Length (m)
1.0	1.70	25 / 125
1.2	1.70	25 / 100
1.5	1.70	25 / 75

Standard panels

Article	Thickness (mm)	Width (m)	Length (m)
RubberTop STT	1.2 / 1.5	3.36 / 5.02 / 6.68 / 8.34 / 10.00 / 11.66 / 13.32 / 14.98	25

Physical properties

For detailed product data, please see corresponding Declaration of Performance.

Storage

Store cool and dry in the original packaging. There are no limitations in shelf life.

Approvals, Certificates & Specifications

CE: EN 13956, BBA.



Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please contact technical department of SealEco.