

TECHNICAL DATA SHEET

RUBBERTOP FLEX

RubberTop Flex is made from an EPDM, reinforced with aluminium expanded metal. The membrane is easy to bend and shape. RubberTop Flex is a very good alternative for lead, it is very strong and has an excellent UV resistance.



Technical data

Thickness	Weight	Colour
2.4 mm	2.8 kg/m ²	Black & grey

Article	Width (mm)	Length (m)	Rolls/Box	Rolls/Pallet	Weight/Roll	Weight/Pallet
RubberTop Flex	100	10	2 rolls/box	360	2.55 Kg	740 Kg
RubberTop Flex	150	10	1 roll/box	200	3.83 Kg	791 Kg
RubberTop Flex	200	10	1 roll/box	160	5.10 Kg	842 Kg
RubberTop Flex	250	10	1 roll/box	120	6.38 Kg	791 Kg
RubberTop Flex	300	10	1 roll/box	100	7.65 Kg	791 Kg
RubberTop Flex	350	10	1 roll/box	80	8.93 Kg	740 Kg
RubberTop Flex	400	10	1 roll/box	80	10.20 Kg	842 Kg
RubberTop Flex	450	10	1 roll/box	70	11.48 Kg	829 Kg
RubberTop Flex	600	10	1 roll/box	50	15.30 Kg	791 Kg

Availability depending on country. Contact your local supplier for more information.

Packaging: All rolls are packed in a separate cardboard box.

Physical properties

For detailed product data, please see corresponding Declaration of Performance.

Storage

Store cool and dry in the original packaging. There are no limitations in shelf life.

Directions for use

The substrate must be clean, dustfree and dry. Application temperature for the application of the adhesives is between +5°C and 30°C. Precipitation, condensation and heavy winds are not allowed during installation. Rubbertop Flex can be cut by means of a knife or with decent scissors. Preform the membrane with a leadhammer or a pressure roller. The minimim overlap shall be 100 mm. Overlaps can be tightened by applying two beads of Ecobond V. Close the overlap and pressure roll until the adhesive comes out from under the overlap. Adhesion to substrates can also be made with Ecobond. Use Primer 9800 on porous substrates.

Approvals, Certificates & Specifications

CE: EN 13956.



Disclaimer

Information contained in this data sheet is up-to-date and correct as at the time of issue. For latest version please always check www.sealeco.com.